

## ATA PPR 1210

### TYPE

Aminofunctional co-reactant for polyisocyanates

### FORM SUPPLIED

Low viscosity, solvent free liquid

### USES

It is suitable for the formulation of tough but flexible, lightfast and highly reactive two-component polyurethane spray coatings.

### MATERIAL SAFETY

SDS for this product is available on request

### APPLICATION

Auto repair

Industrial paints and varnishes

Parquet varnishes

Road marking values. Marine paints and varnishes

Wood

Anti corrosive paint

Floor paint

Furniture varnish

### STORAGE & SHELF LIFE

The material should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C Exposure to direct sunlight should be avoided. Protect from moisture, heat and foreign material. The shelf life of the resin under the mentioned storage conditions is 1 year.

Storage in original sealed Ata yağ ve Kimya container.

The product has the storage time for six months following the day of shipment specified in the relevant transport documents, provided that the product is stored in full compliance with the specified storage conditions.

The passage of six months does not mean that the product no longer meets specifications. However, Ata yağ ve Kimya recommends testing whether such a product meets the specifications before using it.

If this period expires, Ata yağ ve kimya will not make any representation regarding the product and Ata yağ ve kimya will not be responsible or liable in any way if the product does not comply with the specification

### DELIVERY FORM

IBC - 1000 kg

Barrel - 200 kg

Bulk

### TECHNICAL SPECIFICATIONS

| Property                     | Value     | Unit               | Test Method    |
|------------------------------|-----------|--------------------|----------------|
| Amine value                  | 240-255   | mg KOH/g           | DIN 16945      |
| Equivalent weight            | 233-234   | gr/mol             | -              |
| Density (20 °C)              | 1,04-1,08 | gr/cm <sup>3</sup> | DIN 51757      |
| Viscosity (Brookfield 25 °C) | 60-110    | cP                 | TS 6126 EN ISO |
| Flash point                  | >97       | °C                 | -              |
| Water content                | ≤0.1      | %                  | -              |
| Colour                       | Max 250   | Hazen              | TS EN ISO 4630 |
| Solid content                | 95-100    | %                  | TS EN ISO 3251 |

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet