



## ATACRYL 20B60

### PRODUCT DESCRIPTION

Air dried, polyacrylic and thermoplastic resin  
Create fast-drying and easy-to-shape films  
Good resistance to curling and gloss  
Good compatibility with CAB

### CHEMICAL COMPOSITION

Acrylic resin with butyl acetate tolerance

### APPLICATION

Auto repair  
Industrial paints and varnishes  
Road marking  
Wood

### CAN BE APPLIED OVER

Floor paint  
Concrete surfaces  
Metal surfaces

### STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C  
Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

### DELIVERY

IBC - 1000 kg  
Barrel - 200 kg  
Bulk

### MATERIAL SAFETY

SDS for this product is available on request

TECHNICAL SPECIFICATIONS			
Property	Value	Unit	Test Method
Solvent type	Butyl acetate	-	-
Solid content	58-62	%	TS EN ISO 3251
Viscosity (Brookfield 25 °C)	2270-3620	cP	TS 6126 EN ISO 2555
Acid value	Max 11	mg KOH/g	TS 2366 EN ISO 2114
Colour	Max 3	Gardner	TS EN ISO 4630
Density (20 °C)	0,99-1,03	gr/cm <sup>3</sup>	TS EN ISO 2811-1

### SOLUBILITY

Acetone	Soluble
Toluene	Soluble
Xylene	Soluble
Butyl acetate	Soluble
Methyl isobutyl	Soluble

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet

ATA YAĞ VE KİMYA SANAYİ TİCARET ANONİM ŞİRKETİ  
HAYRABOLUOSB MAH. OCAK SK. NO: 3 HAYRABOLU/ TEKİRDAĞ  
[www.atayag.com](http://www.atayag.com)