



ATACRYL 28BA58

PRODUCT DESCRIPTION

Air dried, polyacrylic and thermoplastic resin

Create fast-drying and easy-to-shape films

Good resistance to curling and gloss

CHEMICAL COMPOSITION

Acrylic resin with butyl acetate tolerance

APPLICATION

Auto repair

Industrial paints and varnishes

Road marking

Wood

CAN BE APPLIED OVER

Floor paint

Concrete surfaces

Metal surfaces

STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C
Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

DELIVERY

IBC - 1000 kg

Barrel - 200 kg

Bulk

MATERIAL SAFETY

SDS for this product is available on request

TECHNICAL SPECIFICATIONS			
Property	Value	Unit	Test Method
Solvent type	Butyl acetate	-	-
Solid content	57-59	%	TS EN ISO 3251
Viscosity (Brookfield 25 °C)	6340-14800	cP	TS 6126 EN ISO 2555
Acid value	Max 20	mg KOH/g	TS 2366 EN ISO 2114
Colour	Max 2	Gardner	TS EN ISO 4630
Density (20 °C)	0,99-1,03	gr/cm ³	TS EN ISO 2811-1

SOLUBILITY

Acetone	Soluble
Toluene	Soluble
Xylene	Soluble
White spirit	Insoluble
Butyl acetate	Soluble
Methyl isobutyl	Soluble

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet