

**ATACRYL 30B55****PRODUCT DESCRIPTION**

Air dried, polyacrylic and thermoplastic resin  
Create fast-drying and easy-to-shape films  
Good resistance to curling and gloss

**STORAGE & SHELF LIFE**

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

**CHEMICAL COMPOSITION**

Acrylic resin with butyl acetate tolerance

**DELIVERY**

IBC - 1000 kg  
Barrel - 200 kg  
Bulk

**APPLICATION**

Auto repair  
Industrial paints and varnishes  
Road marking  
Wood  
Floor paint

**MATERIAL SAFETY**

SDS for this product is available on request

**CAN BE APPLIED OVER**

Concrete surfaces  
Metal surfaces

**TECHNICAL SPECIFICATIONS**

| Property                     | Value         | Unit               | Test Method         |
|------------------------------|---------------|--------------------|---------------------|
| Solvent type                 | Butyl acetate | -                  | -                   |
| Solid content                | 54-56         | %                  | TS EN ISO 3251      |
| Viscosity (Brookfield 25 °C) | 627-1290      | cP                 | TS 6126 EN ISO 2555 |
| Acid value                   | Max 12        | mg KOH/g           | TS 2366 EN ISO 2114 |
| Colour                       | Max 2         | Gardner            | TS EN ISO 4630      |
| Density (20 °C)              | 0,96-1,00     | gr/cm <sup>3</sup> | TS EN ISO 2811-1    |

**SOLUBILITY**

|                 |         |
|-----------------|---------|
| Acetone         | Soluble |
| Toluene         | Soluble |
| Xylene          | Soluble |
| Butyl acetate   | Soluble |
| Methyl isobutyl | Soluble |

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet