



## ATAKYD MO 51WX55

## PRODUCT DESCRIPTION

Solvent based, medium oil and oxidative drying alkyd resin

High yellowing resistance

High colour durability and gloss retention

## STORAGE &amp; SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged

container in a dry place at storage temperature between 5-30 °C

Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

## COMPATIBILITY

Long and medium oil alkyd resins

Compatible

## DELIVERY FORM

IBC - 900 kg

Barrel - 185 kg

Bulk

## APPLICATION

Auto repair

Industrial paints and varnishes

Road marking

Synthetic paints and varnishes

## MATERIAL SAFETY

SDS for this product is available on request

## TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Modification	Specific	-	-
Type of oil	TOFA	-	-
Oil percentage	51	%	-
Solvent type	White spirit / Xylene	-	-
Solid content	54-56	%	TS EN ISO 3251
Viscosity (Gardner 25 °C, %55 Solid)	Y-Z2 / 26,8-53,1	Gardner/sec	ASTM D 1545-13
Acid value	Max 12	mg KOH/g	TS 2366 EN ISO 2114
Density (20 °C)	0,93-0,96	gr/cm <sup>3</sup>	TS EN ISO 2811-1
Colour (% 50 Solid)	Max 5	Gardner	TS EN ISO 4630

## SOLUBILITY

Acetone	Soluble
White spirit	Soluble
Toluene	Soluble
Xylene	Soluble

## RECOMMENDED DRYER RATES

Cobalt	0,04-0,06 %
Zirconium	0,25-0,45 %
Calcium	0,15-0,35 %

Recommended scatter rates over 100% solid alkyd metal percentages.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet