



ATAKYD RAP 26T60 LV

PRODUCT DESCRIPTION

Solvent based, short oil and oxidative drying alkyd resin

High yellowing resistance

High colour durability and gloss retention

STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

COMPATIBILITY

Long oil alkyd resins	Incompatible
Amino resins	Compatible
Short oil alkyd resins	Compatible
Cellulose nitrate	Compatible
Aromatic polyisocyanate	Compatible

DELIVERY FORM

IBC - 1000 kg
Barrel - 200 kg
Bulk

APPLICATION

Auto repair
Industrial paints and varnishes
Road marking
Hammerton paints

MATERIAL SAFETY

SDS for this product is available on request

TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Modification	Benzoic acid	-	-
Type of oil	Soybean oil	-	-
Oil percentage	26	%	-
Solvent type	Toluene	-	-
Solid content	59-61	%	TS EN ISO 3251
Viscosity (Gardner 25 °C)	W-Y / 15,7-26,8	Gardner/sec	ASTM D 1545-13
Acid value	Max 11	mg KOH/g	TS 2366 EN ISO 2114
Density (20 °C)	0,98-1,02	gr/cm ³	TS EN ISO 2811-1
Colour (%50 Solid)	Max 7	Gardner	TS EN ISO 4630

SOLUBILITY

Acetone	Soluble	Cobalt	0,03-0,06 %
White spirit	Insoluble	Zirconium	0,15-0,30 %
Toluene	Soluble	Calcium	0,10-0,20 %
Xylene	Soluble	Recommended scatter rates over 100% solid alkyd metal percentages.	
Terebentine	Insoluble		

RECOMMENDED DRYER RATES

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet