



## ATAKYD RAP 31X65

## PRODUCT DESCRIPTION

Solvent based, short oil and oxidative drying alkyd resin  
High yellowing resistance  
High colour durability and gloss retention

## STORAGE &amp; SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C  
Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

## COMPATIBILITY

Amino resins	Compatible
Short oil alkyd resins	Compatible
Cellulose nitrate	Compatible
Aromatic polyisocyanate	Compatible
Long oil alkyd resins	Incompatible
Medium oil alkyd resins	Partial

## DELIVERY FORM

IBC - 1000 kg  
Barrel - 200 kg  
Bulk

## APPLICATION

Auto repair  
Industrial paints and varnishes  
Road marking  
Hammerton paints

## MATERIAL SAFETY

SDS for this product is available on request

## TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Modification	Benzoic acid	-	-
Type of oil	TOFA	-	-
Oil percentage	31	%	-
Solvent type	Xylene	-	-
Solid content	64-66	%	TS EN ISO 3251
Viscosity (Gardner 25 °C)	Z4-Z6 / 93-217,1	Gardner/sec	ASTM D 1545-13
Acid value	Max 11	mg KOH/g	TS 2366 EN ISO 2114
Density (20 °C)	1,07-1,10	gr/cm <sup>3</sup>	TS EN ISO 2811-1
Colour (%50 Solid)	Max 5	Gardner	TS EN ISO 4630

## SOLUBILITY

Acetone	Soluble
White spirit	Insoluble
Toluene	Soluble
Xylene	Soluble
Terebentine	Insoluble

## RECOMMENDED DRYER RATES

Cobalt	0,03-0,06 %
Zirconium	0,15-0,30 %
Calcium	0,10-0,20 %
Recommended scatter rates over 100% solid alkyd metal percentages.	

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet