

**ATAKYD URAL 63W60****PRODUCT DESCRIPTION**

TDI modified solvent based oxidative drying alkyd resin
 High yellowing resistance
 High colour durability and gloss retention

STORAGE & SHELF LIFE

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C
 Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year.

COMPATIBILITY

Long oil alkyd resins	Compatible
Short oil alkyd resins	Incompatible
Amino resins	Compatible

DELIVERY FORM

IBC - 900 kg
Barrel - 185 kg
Bulk

APPLICATION

Parquet varnishes
 Marine paints and varnishes
 Wood
 Anti corrosive paint
 Industrial paints and varnishes

MATERIAL SAFETY

SDS for this product is available on request.

TECHNICAL SPECIFICATIONS

Property	Value	Unit	Test Method
Modification	TDI	-	-
Type of oil	Soybean oil	-	-
Oil percentage	63	%	-
Solvent type	White spirit	-	-
Solid content	59-61	%	TS EN ISO 3251
Viscosity (Gardner 25 °C)	Z-Z2 / 33,3-53,1	Gardner/sec	ASTM D 1545-13
Acid value	Max 4	mg KOH/g	TS 2366 EN ISO 2114
Density (20 °C)	0,93-0,96	gr/cm ³	TS EN ISO 2811-1
Colour (%50 Solid)	Max 6	Gardner	TS EN ISO 4630

SOLUBILITY

Acetone	Soluble	Cobalt
White spirit	Soluble	Zirconium
Toluene	Soluble	Calcium
Xylene	Soluble	

RECOMMENDED DRYER RATES

0,04-0,06 %
0,25-0,45 %
0,15-0,35 %
Recommended scatter rates over 100% solid alkyd metal percentages.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet