

SYNTHETIC RESINS – PAINT AND VARNISH / Solvent-Based**EPOXY HARDENER / POLYAMINE**

ATAMIN CA 35 N

PRODUCT DESCRIPTION

Excellent adhesion to metal and mineral surfaces,
Outstanding pigment and substrate wetting,
Good chemical resistance,
Excellent color.

PACKING

IBC-1000 KG
VARİL-200 KG
Bulk

TECHNICAL SPECIFICATIONS

Specification	Value	Unit	Test Method
Amine value	350-450	mg KOH/g	DIN 16954
Viscosity (Brookfield 75 °C)	200-350	cP	DINEN ISO 3219/A-3
Color	Max 2	Gardner	TS EN ISO 4630
Density (20 °C)	1,00-1,04	g/cm ³	TS EN ISO 2811-1
Amine hydrogen equivalent weight	Yaklaşık 104	g/mol	-
minute)	20-30	fr.20->40°Cw.	DIN EN 22719

STORAGE CONDITIONS AND SHELF LIFE

The material should be stored in its original, unopened, and undamaged container in a dry place at temperatures between 5–30 °C. It must be protected from direct sunlight. Avoid exposure to moisture, heat, and foreign substances. Under the specified storage conditions, the resin's shelf life is 1 year.