

ATAMIN CA 46

PRODUCT DESCRIPTION

Excellent water and corrosion resistance,
Excellent adhesion,
Excellent pigment and substrate wetting,
Good chemical resistance,
Long pot life,
Fast drying

APPLICATIONS

Industrial coatings and varnishes, Enamel stoving paints
Road marking paints, Can and coil coatings
Decorative coatings

PACKING

IBC-1000 KG
VARİL-200 KG
Bulk

TECHNICAL SPECIFICATIONS

Specification	Value	Unit	Test Method
Amine value	350-450	mg KOH/g	DIN 16954
Viscosity (Brookfield 75 °C)	200-350	cP	DINEN ISO 3219/A-3
Color	Max 2	Gardner	TS EN ISO 4630
Density (20 °C)	1,00-1,04	g/cm ³	TS EN ISO 2811-1
Amine hydrogen equivalent weight	Aprox. 93	g/mol	-
minute)	20-30	fr.20->40°Cw.	DIN EN 22719
Flash point	>100	°C	-

STORAGE CONDITIONS AND SHELF LIFE

The material should be stored in its original, unopened, and undamaged container in a dry place at temperatures between 5–30 °C. It must be protected from direct sunlight. Avoid exposure to moisture, heat, and foreign substances. Under the specified storage conditions, the resin's shelf life is 1 year.