

SYNTHETIC RESINS – PAINTS AND VARNISHES / Solvent-Based EPOXY RESIN HARDENER / POLYAMIDE RESIN**ATAMID 15X70 LV****PRODUCT DESCRIPTION**

Excellent water and corrosion resistance
Outstanding adhesion
Superior pigment and surface wetting
Good chemical resistance
Long shelf life
Fast drying

APPLICATIONS

Industrial paints and varnishes, Wood coatings
Road marking paints, Can and coil coatings,
Decorative coatings

PACKING

IBC-1000 KG
DRUM-200 KG
Bulk

TECHNICAL SPESIFICATIONS

Specifications	Value	Unit	Test Method
Amine value	160-240	mg KOH/g	DIN 16954
Solvent type	Ksilen	-	-
Viscosity (Brookfield 25 °C)	400-600	cP	DINEN ISO 3219/A-3
Solid Content	69-71	%	TS EN ISO 3251
Color	Maksimum 12	Gardner	TS EN ISO 4630
Density (20 °C)	0,94-0,98	g/cm ³	TS EN ISO 2811-1
Amine Hydrogen Equivalent Weight	210-230	g/mol	-
Pot life	80-100	dk	-
Flash Point	27	°C	-

STORAGE CONDITIONS AND SHELF LIFE

The material should be stored in its original, unopened, and undamaged container in a dry place at temperatures between 5–30 °C. It must be protected from direct sunlight. Avoid exposure to moisture, heat, and foreign substances. Under the specified storage conditions, the resin's shelf life is 1 year.